Carbonless CF

Facestock

Carbonless CF

Description Bottom sheet (CF) of the carbonless form containing a layer of activated clay on the front.

Color White

Applications Extensively used in shipment forms when last sheet must be self-adhesive.

Printing techniques Suitable for printing on conventional offset, offset UV, letterpress (conventional and UV), flexo (all types).

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	57	± 4%
Thickness	ISO534	μm	66	± 5
Bekk smoothness	ISO 5627	s	≥ 50	
Whiteness CIE	ISO 11475	°CIE	99	± 6
Opacity	ISO 2471	%	80	-4

Values are subject to change without notice. Last updated 1/1/2024.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.

^{*} The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.