## Acetate Clear

Facestock

## Acetate Clear

Description	Clear	glossy	tear	-resistant	cellulose	acetate	film.
-------------	-------	--------	------	------------	-----------	---------	-------

Color Clear

Finish Gloss

Applications Clear labels predominantly used for cosmetics and quality indoor advertising. Not suitable for outdoor use due to extreme sensitivity to harsh weather conditions and/or solvents.

Printing techniques Suitable for printing on UV flexo, offset UV, conventional offset, letterpress (conventional and UV), hot stamping, screen printing.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	65	62.2-68.8
Thickness	ISO 534	μm	50	46-54
Dimensional stability 100°C 10min MD	ASTM D 1204	%	-1	± 1
Dimensional stability 100°C 10min CD	ASTM D 1204	%	-1	± 1

\* Values are subject to change without notice. Last updated 1/1/2024.

\* The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.