

# ADESTOR Laid WS White / A251 / YG62

FACESTOCK

## Laid WS White

*Description* Uncoated wet-strength woodfree laid paper with a textured finish.

*Color* White

*Applications* Specially designed for prestige labels for wine, spirits and gourmet products.

*Printing techniques* Suitable for printing on offset UV, conventional offset, screen printing, hot stamping, flexo solvent-base, UV flexo, flexo water-based.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m <sup>2</sup>	80	77 - 84
Thickness	ISO 534	µm	100	92 -105
Tensile strength MD/CD	ISO 1924	kN/m	≥ 3,3 / ≥ 1,8	

ADHESIVE

## A251

*Description* General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.

*Shelf life* From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	15,4	≥ 12,3
Shear (1kg, in <sup>2</sup> /glass)	FTM 8	min	100	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	10,3	≥ 7,8
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

LINER

## YG62

*Description* Super-calendered yellow translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

*Color* Yellow

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m <sup>2</sup>	62	59-65
Thickness	ISO 534	µ	52	50-58

## Certificates

Product approvals and usage certificates

ADHESIVE

## A251

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

EN 71-9 Toy safety

Direct contact with foodstuffs (ISEGA) - Adhesives

LINER

**YG62**

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

- Values are subject to change without notice. Last updated 3/15/2016.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.