Gloss 125 / PC491 / WK80

Facestock

Gloss 125

Description High substance gloss coated woodfre paper.

Applications For automatic labelling of meal trays thanks to its extra substance.

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, screen printing, hot stamping, thermal transfer, laser.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	125	± 4%
Thickness	ISO 534	μm	91	± 4%
Bekk smoothness	ISO 5627	s	1100	± 40%
Brightness ISO	ISO 2470-2	%	95.2	± 2
Whiteness CIE	ISO 11475	%	119	± 3
Paper gloss 20°	ISO 8254-1	%	72	± 5
Opacity	ISO 2471	%	93.5	-2

Adhesive

PC491

Acrylic semipermanent adhesive with high cohesion and medium adhesion and tack that permits repositioning upon application. Especially designed for stickers (promotions, collections, games). Shelf life From the date of manufacture 2 years in +20°C and RH 50%.

Property Norm Units Value **Tolerance** FTM 1 N/25mm 9,1 ≥ 7,4 FTM 9 Ν 4,7 ≥ 3,2 FTM 8 min 50 ≥ 30

Adhesion (Peel 180º 20'/stainless steel) Tack (Quick Stick stainless steel) Shear (1kg, in²/glass) ٥С Minimum labelling temperature +5 ٥С -20 Minimum service temperature ٥С Maximum service temperature. +80

Liner

Kraft White 80

One-side coated white liner with good lay-flat characteristics. Suitable for sheeting. Available only

Color White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	80	± 4%
Thickness	ISO 534	μm	81	± 4
Tensile strength MD/CD	ISO 1924-2	kN/m	4,6/2,3	-0,6/-0,3

Values are subject to change without notice. Last updated 1/1/2024.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.