

ADESTOR Embossed Martelé / BC361 Plus / WG80

FACESTOCK

Embossed Martelé WS

Description One side embossed wet-strength coated paper with a martelé finishing.

Color White

Applications Prestige labels for wine and delicatessen products.

Printing techniques Suitable for printing on UV flexo, offset UV, UV letterpress.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	90	± 4
Thickness	ISO 534	µm	120	± 9
Opacity	ISO 2471	%	92	
Tensile strength	ISO 1924-2	N/15mm	70	min. 60

ADHESIVE

BC361 Plus

Description Acrylic permanent adhesive for non-recyclable bottles. The printed label resists a minimum of 2 hours with the bottle being submerged ice water (Ice Test)

Shelf life From the date of manufacture, 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	11,5	≥ 9,1
Shear (1kg, in ² /glass)	FTM 8	min	28	≥ 18
Tack (Quick Stick stainless steel)	FTM 9	N	10,1	≥ 7,8
Minimum labelling temperature		°C	-20	
Minimum service temperature		°C	-30	
Maximum service temperature.		°C	+60	

LINER

WG80

Description Super-calendered white translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color White

Applications For those applications where extra thickness of the backing paper is required such as wine labelling and filmic applications.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	77-83
Thickness	ISO 534	µm	68	64-72

Certificates

Product approvals and usage certificates

ADHESIVE

BC361 Plus

Direct contact with foodstuffs (ISEGA) - Adhesives

LINER

WG80

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

- Values are subject to change without notice. Last updated 1/20/2016.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.