

ADESTOR Gloss 60 / SP123 / WG62

FACESTOCK

Gloss 60

Description Low substance gloss coated woodfree paper.

Color White

Finish Gloss

Applications For small diameter containers and the food sector.

Printing techniques Suitable for printing on flexo (all types), conventional offset, offset UV, hot stamping, laser, screen printing, thermal transfer, letterpress (conventional and UV).

Property	Norm	Units	Value	Tolerance
Substance	ISO 536		60	57.6 - 62.4
Thickness			52	48-56
Bekk smoothness			≥ 600	
Brightness ISO			90	87-93
Opacity			76-83	
Paper gloss 20°			85	± 5
Tensile strength MD/CD	ISO 1924	kN/m	≥ 3 / ≥ 1.7	

ADHESIVE

SP123

Description Acrylic super-permanent adhesive with high tack. For difficult surfaces such as wood, some cardboards and plastics such as HDPE, PP, PET and PVC.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	17,2	≥ 13,5
Shear (1kg, in ² /glass)	FTM 8	min	100	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	11	≥ 9,8
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

LINER

WG62

Description Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	62	59-65
Thickness	ISO 534	µm	52	49-55

Certificates

Product approvals and usage certificates

ADHESIVE

SP123

EN 71-3 Toy safety

EN 71-9 Toy safety

Packaging and packaging waste Directive 94/62/CE

German Recommendation BfR XIV (ISEGA) - Adhesives

LINER

WG62

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

- Values are subject to change without notice. Last updated 3/15/2016.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.