

# ADESTOR Gloss Opaque 80 / SP123 / YG62

FACESTOCK

## Gloss Opaque 80

*Description* Gloss coated woodfree paper with an opaque treatment on the reverse.

*Applications* High resolution standard gloss label used to block-out existing printed information (i.e. prices).

*Printing techniques* Suitable for printing on flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, hot stamping, thermal transfer, laser.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m <sup>2</sup>	80	±4%
Thickness	ISO 534	µm	61	±6%
Bekk smoothness	ISO 5627	s	≥850	
Opacity	ISO 2471	%	99.7	

## ADHESIVE

### SP123

*Description* Acrylic super-permanent adhesive with high tack. For difficult surfaces such as wood, some cardboards and plastics such as HDPE, PP, PET and PVC.

*Shelf life* From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	17,2	≥ 13,5
Shear (1kg, in <sup>2</sup> /glass)	FTM 8	min	100	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	11	≥ 9,8
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

## LINER

### YG62

*Description* Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

*Color* Yellow

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m <sup>2</sup>	62	59-65
Thickness	ISO 534	µ	52	50-58

## Certificates

Product approvals and usage certificates

ADHESIVE

## SP123

EN 71-3 Toy safety

EN 71-9 Toy safety

Packaging and packaging waste Directive 94/62/CE

German Recommendation BfR XIV (ISEGA) - Adhesives

LINER

## YG62

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

- Values are subject to change without notice. Last updated 3/14/2016.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.