

# Thermal Eco

Facestock

## Thermal Eco

*Description*

*Applications* Variable information labelling in dry environments such as POS price marking and barcodes generally for shipping forms, logistics and dispatch.

Property	Norm	Units	Value	Tolerance
Substance			74	± 4%
Thickness			82	± 5
Bekk smoothness			325	≥ 200
Whiteness CIE			114	± 6
Tensile strength MD/CD			5,2 / 2,7	≥ 4,4 / ≥ 2,0

- Values are subject to change without notice.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.