

Offset PiggyBack

Facestock

Offset PiggyBack

Description Complex formed by Offset facestock (calendered uncoated woodfree paper), A251 permanent adhesive and yellow glassine liner 62 gsm.

Applications Extensively used in logistics for shipping and courier applications.

Printing techniques Suitable for printing on flexo (all types), conventional offset, offset UV, letterpress (conventional and UV), screen printing, thermal transfer, hot stamping, laser.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	135	70-76
Thickness	ISO 534	µm	137	± 2
Bekk smoothness	ISO 5627	s	≥250	
Brightness ISO	ISO 2470-2	%	101.5	± 2
Whiteness CIE	ISO 11475	%	158.2	± 5
Opacity	ISO 2471	%	89	-2
Wet tensile strength MD/CD	ISO 1924-2	kN/m	5.0/3.0	-1

Values are subject to change without notice. Last updated 7/12/2018.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.