

Offset / A251 / WK130

Facestock

Offset

Description Calendered uncoated woodfree paper.

Applications Ideal for all types of applications: variable label information (barcodes, expiry date, price, weight etc.)

Printing techniques Suitable for printing on flexo (all types), conventional offset, offset UV, letterpress (conventional and UV), screen printing, thermal transfer, laser, hot stamping.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	68	± 5
Thickness	ISO 534	µm	65	± 2
Bekk smoothness	ISO 5627	s	≥ 225	
Whiteness CIE	ISO 11475	%	152	± 5
Opacity	ISO 2471	%	86	-2
Tensile strength MD/CD	ISO 1924-2	kN/m	4 / 2	-1

Adhesive

A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	15,4	≥ 7,8
Tack (Quick Stick stainless steel)	FTM 9	N	10,3	≥ 7,8
Shear (1kg, in ² /glass)	FTM 8	min	100	≥ 60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

Liner

Kraft White 130

Description One-side coated white liner with high stiffness and stability. Available in split and solid back.

Color White

Applications Specially indicated for filmic applications.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	128	123 - 133
Thickness	ISO 534	µm	124	119 - 129
Tensile strength MD/CD	ISO 1924-2	kN/m	≥6,3 / ≥3,5	

* Values are subject to change without notice. Last updated 1/1/2025.

* The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards **ISO 14001** and **EMAS** and has successfully completed audits for **ISO 50001**, **ISO 9001** and **ISO 45001** certification. Adestor paper products are available with **PEFC** and **FSC®** C011032 chain of custody certificates upon request.