

ADESTOR Gloss Opaque 80 / A251 / YG62

FACESTOCK

Gloss Opaque 80

Description Gloss coated woodfree paper with an opaque treatment on the reverse.

Applications High resolution standard gloss label used to block-out existing printed information (i.e. prices).

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, hot stamping, thermal transfer, laser.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	±4%
Thickness	ISO 534	µm	61	±6%
Bekk smoothness	ISO 5627	s	≥850	
Opacity	ISO 2471	%	99.7	

ADHESIVE

A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	15,4	≥ 12,3
Shear (1kg, in ² /glass)	FTM 8	min	100	≥ 60
Tack (Quick Stick stainless steel)	FTM 9	N	10,3	≥ 7,8
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

LINER

YG62

Description Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color Yellow

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	62	59-65
Thickness	ISO 534	µ	52	50-58

Certificates

Product approvals and usage certificates

ADHESIVE

A251

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

EN 71-9 Toy safety

German Recommendation BfR XIV (ISEGA) - Adhesives

LINER

YG62

Contact with foodstuff (BfR XXXVI) - Facestock and Liners (paper)

Packaging and packaging waste Directive 94/62/CE

EN 71-3 Toy safety

Electric and electronic equipment (RoHS)

Values are subject to change without notice. Last updated 2/11/2016.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.