

Matt 80 / PC491 / WK130

Facestock

Matt 80

Description Matt coated woodfree paper.

Applications Standard label applications with matt finish.

Printing techniques Suitable for printing on laser, flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, screen printing, hot stamping.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	± 4%
Thickness	ISO 534	µm	74	± 4%
Bekk smoothness	ISO 5627	s	≤100	
Brightness ISO	ISO 2470-2	%	96	± 2
Whiteness CIE	ISO 11475	%	119	± 3
Opacity	ISO 2471	%	90	-2

Adhesive

PC491

Description Acrylic semipermanent adhesive with high cohesion and medium adhesion and tack that permits repositioning upon application. Especially designed for stickers (promotions, collections, games).

Shelf life From the date of manufacture 2 years in +20°C and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	9,1	≥ 7,4
Tack (Quick Stick stainless steel)	FTM 9	N	4,7	≥ 3,2
Shear (1kg, in ² /glass)	FTM 8	min	50	≥ 30
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

Liner

Kraft White 130

Description One-side coated white liner with high stiffness and stability. Available in split and solid back.

Color White

Applications Specially indicated for filmic applications.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	128	123 - 133
Thickness	ISO 534	µm	124	119 - 129
Tensile strength MD/CD	ISO 1924-2	kN/m	≥6,3 / ≥3,5	

* Values are subject to change without notice. Last updated 01/01/2025.

* The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards **ISO 14001** and **EMAS** and has successfully completed audits for **ISO 50001**, **ISO 9001** and **ISO 45001** certification. Adestor paper products are available with **PEFC** and **FSC®** C011032 chain of custody certificates upon request.