# PE Transparent 100µm / A251 / WG62

Facestock

### PE Gloss Clear TC100

Description Clear gloss top-coated polyethylene. High resistance to water, chemicals and UV light.

Color Clear

Finish Gloss

Applications For labelling cosmetics, toiletries: suitable for squeezable containers. Can also be used for outdoor

applications.

Printing techniques Suitable for printing on UV flexo, offset UV, conventional offset, letterpress (conventional and UV),

screen printing, hot stamping.

| Norm        | Units  | Value   | Tolerance   |
|-------------|--|---|---|
| DIN 53352   | g/m²   | 94  | ± 8   |
| DIN 53370   | μm   | 100   | ± 8   |
| DIN 67530   | %  | > 80  |   |
| ISO 527     | MPa  | 17-23/18.5-21.5   |   |
| DIN 53364   | dina/cm  | ≥ 38  |   |
| ASTM D 1204 | %  | -3  | ± 3   |
| ASTM D 1204 | %  | - 2   | ± 2   |
|             | DIN 53352<br>DIN 53370<br>DIN 67530<br>ISO 527<br>DIN 53364<br>ASTM D 1204 | DIN 53352 g/m² DIN 53370 μm DIN 67530 % ISO 527 MPa DIN 53364 dina/cm ASTM D 1204 % | $DIN 53352$ $g/m^2$ 94<br>DIN 53370 $μm$ 100<br>DIN 67530 % > 80<br>ISO 527 $MPa$ 17-23/18.5-21.5<br>DIN 53364 $dina/cm$ ≥ 38<br>ASTM D 1204 % -3 |

## Adhesive

### A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces. Shelf life From the date of manufacture 2 years in 20°C and RH 50%

| Property                                 | Norm  | Units  | Value | Tolerance |
|--|-------|--------|-------|-----------|
| Adhesion (Peel 180° 20'/stainless steel) | FTM 1 | N/25mm | 15,4  | ≥ 7,8     |
| Tack (Quick Stick stainless steel)       | FTM 9 | N      | 10,3  | ≥ 7,8     |
| Shear (1kg, in²/glass)                   | FTM 8 | min    | 100   | ≥ 60      |
| Minimum labelling temperature            |       | °C     | +5    |           |
| Minimum service temperature              |       | °C     | -20   |           |
| Maximum service temperature.             |       | °C     | +80   |           |

Liner

## Glassine White 62

Super-calendered translucent glassine paper especially designed for automatic labelling Description applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color White

| Property  | Norm    | Units | Value | Tolerance |
|-----------|---------|-------|-------|-----------|
| Substance | ISO 536 | g/m²  | 62    | 59 - 65   |
| Thickness | ISO 534 | um    | 52    | 51 - 59   |



- Values are subject to change without notice. Last updated 01/01/2024.
- \* The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.