

# Carbonless CF

Facestock

## Carbonless CF

*Description* Bottom sheet (CF) of the carbonless form containing a layer of activated clay on the front.

*Color* White

*Applications* Extensively used in shipment forms when last sheet must be self-adhesive.

*Printing techniques* Suitable for printing on conventional offset, offset UV, letterpress (conventional and UV), flexo (all types).

| Property        | Norm      | Units            | Value | Tolerance |
|-----------------|-----------|------------------|-------|-----------|
| Substance       | ISO 536   | g/m <sup>2</sup> | 57    | ± 4%      |
| Thickness       | ISO534    | µm               | 66    | ± 5       |
| Bekk smoothness | ISO 5627  | s                | ≥ 50  |           |
| Whiteness CIE   | ISO 11475 | °CIE             | 99    | ± 6       |
| Opacity         | ISO 2471  | %                | 80    | -4        |

## Certificates

### Product approvals and usage certificates

Packaging and packaging waste Directive 94/62/CE

Electric and electronic equipment (RoHS)

Values are subject to change without notice. Last updated 1/1/2022.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards **ISO 14001 and EMAS** and has successfully completed audits for **ISO 50001, ISO 9001 and ISO 45001** certification. Adestor paper products are available with **PEFC and FSC® C011032** chain of custody certificates upon request.