Supertack

Adhesive

Supertack

Specially strong and agressive acrylic permanent adhesive with excellent tack and final Description adhesion. For difficult surfaces such as wood boxes, slightly wet surfaces, rough plastics and LDPF

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180º 20'/stainless steel)	FTM 1	N/25mm	14	≥ 11,5
Adhesion (Peel 180° 24h/kraft)	FTM 1	N/25mm	7,6	≥ 6,6
Adhesion (Peel 180° 24h/LDPE)	FTM 1	N/25mm	250	≥ 5,4
Tack (Quick Stick stainless steel)	FTM 9	N	12,3	≥ 9,8
Shear (1kg, in²/glass)	FTM 8	min	15	≥ 10
Minimum labelling temperature		°C	-7	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+60	

Values are subject to change without notice. Last updated 1/1/2024.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.

^{*} The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.