# Laid Cream 90 WS / A251 / GA 62

Facestock

## Laid Cream 90 WS

Description Uncoated wet-strength woodfree laid paper with a textured finish.

Color Cream

Applications Specially designed for prestige labels for wine, spirits and gourmet products.

We recommend winding the labels reels with the face side out.

Printing techniques Suitable for printing on conventional offset, offset UV, screen printing, hot stamping, flexo water-based, flexo solvent-base, UV flexo.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	90	± 4%
Thickness	ISO 534	μm	123	± 5%
Tensile strength MD/CD	ISO 1924	kN/m	≥ 7/ ≥ 4	

## Adhesive

## A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces. Shelf life From the date of manufacture 2 years in 20°C and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	15,4	≥ 7,8
Tack (Quick Stick stainless steel)	FTM 9	N	10,3	≥ 7,8
Shear (1kg, in²/glass)	FTM 8	min	100	≥ 60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

#### Liner

## Glassine Ambar 62

Super-calendered translucent glassine paper especially designed for automatic labelling Description applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color Yellow

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	56	55-57
Thickness	ISO 534	μ	48	46 - 49

Values are subject to change without notice. Last updated 1/1/2025.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline