# Fluo Orange / A251 / WK80

Facestock

## Fluor Orange

Description Matt coated woodfree paper with an orange fluorescent coating.

Color Orange

Applications Eye-catching labels for pricing, display, promotions and warning signs.

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), hot stamping, laser, conventional offset, offset UV, screen printing, thermal transfer.

Norm	Units	Value	Tolerance
ISO 536	g/m²	80	76-84
ISO 534	μm	82	77-87
ISO 5627	s	250	≥ 200
ISO 1924	kN/m	5,5/2,6	≥ 4,5/ ≥ 2,2
TAPPI UM 427	mm	≤30 mm	
	ISO 536 ISO 534 ISO 5627 ISO 1924	ISO 536 g/m² ISO 534 µm ISO 5627 s ISO 1924 kN/m	ISO 536 g/m² 80 ISO 534 μm 82 ISO 5627 s 250 ISO 1924 kN/m 5,5/2,6

#### Adhesive

## A251

Description General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces. Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	15,4	≥ 7,8
Tack (Quick Stick stainless steel)	FTM 9	N	10,3	≥ 7,8
Shear (1kg, in²/glass)	FTM 8	min	100	≥ 60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

Liner

# Kraft White 80

Description One-side coated white liner with good lay-flat characteristics. Suitable for sheeting. Available only in solid back

Color White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m²	80	± 4%
Thickness	ISO 534	μm	81	± 4
Tensile strength MD/CD	ISO 1924-2	kN/m	4,6/2,3	-0,6/-0,3

Values are subject to change without notice. Last updated 1/1/2024.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.

The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.