

# Vellum / SA234 / GA 62

Facestock

## Vellum

*Description* Calendered uncoated woodfree paper.

*Color* White

*Finish* Matt

*Applications* Ideal for all types of applications: variable label information (barcodes, expiry date, price, weight etc.)

*Printing techniques* Suitable for printing on flexo (all types), conventional offset, offset UV, Dry toner, thermal transfer.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m2	75	± 5
Thickness	ISO 534	µm	70	± 2
Whiteness CIE	ISO 11475	%	158.2	± 5
Opacity	ISO 2471	%	89	-2
Tensile strength MD/CD	ISO 1924-2	kN/m	5.0/3.0	-1

Adhesive

## SA234

*Description* Water removable adhesive with high cohesion and medium adhesion and tack. Ideal for labelling different types of reusable transport boxes and trays in logistics and other surfaces (\*) used in retail such as glass, ceramic, plastic.  
 (\*) Face stock material, substrate surface tension or end use conditions are factors that influence on the washing results.

*Shelf life* From the date of manufacture 2 years in +20°C and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	12	>12
Adhesion (Peel 180° 24h/kraft)	FTM 1	N/25mm	5	>5
Adhesion (Peel 180° 24h/PE)	FTM 1	N/25mm	4	>4
Tack (Quick Stick stainless steel)	FTM 9	N	7	>7
Shear (1kg, in <sup>2</sup> /glass)	FTM 8	min.	60	>60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-30	
Maximum service temperature.		°C	+60	

Liner

## Glassine Ambar 62

*Description* Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

*Color* Yellow

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m <sup>2</sup>	62	59-65
Thickness	ISO 534	μ	52	50-58

- Values are subject to change without notice. Last updated 1/1/2023.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.