

PVC Blanco / SA234 / KB130

Facestock

PVC Gloss White

Description Monomeric plasticised polyvinyl-chloride film with good dimensional stability.

Color White

Finish Gloss

Applications Used in a variety of applications: POS promotional, eye-catching and warning labels. Suitable for indoor and also for outdoor short-term campaigns.

Printing techniques Suitable for printing on UV flexo, conventional offset, letterpress (conventional and UV), hot stamping, Inkjet (solvent, mild solvent, UV and latex).

Property	Norm	Units	Value	Tolerance
Substance	ASTM D 1593	g/m ²	110	104.4 - 115.4
Thickness	ASTM D 1593	µm	80	72-88
Gloss 60°	ASTM D 523	%	> 80	≥ 65
Surface tension	DIN 53364	dina/cm	≥ 36	
Dimensional stability 100°C 10min MD	ASTM D 1204	%	-5	5
Dimensional stability 100°C 10min CD	ASTM D 1204	%	-2	± 2

Adhesive

SA234

Water removable adhesive with high cohesion and medium adhesion and tack. Ideal for labelling different types of reusable transport boxes and trays in logistics and other surfaces (*) used in retail such as glass, ceramic, plastic.

Description (*) Face stock material, substrate surface tension or end use conditions are factors that influence on the washing results.

Shelf life From the date of manufacture 2 years in +20°C and RH 50%.

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	12	>12
Adhesion (Peel 180° 24h/kraft)	FTM 1	N/25mm	5	>5
Adhesion (Peel 180° 24h/PE)	FTM 1	N/25mm	4	>4
Tack (Quick Stick stainless steel)	FTM 9	N	7	>7
Shear (1kg, in ² /glass)	FTM 8	min.	60	>60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-30	
Maximum service temperature.		°C	+60	

Liner

Kraft White 130

Description One-side coated white liner with high stiffness and stability. Available in split and solid back.

Color White

Applications Specially indicated for filmic applications.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	130	124,8 - 135,2
Thickness	ISO 534	µm	134	124 - 144
Tensile strength MD/CD	ISO 1924-2	kN/m	≥6,7 / ≥4,3	

- Values are subject to change without notice. Last updated 01/01/2024.
- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.