

# Laid Cream 90 WS / A251 / GA 62

Facestock

## Laid Cream 90 WS

*Description* Uncoated wet-strength woodfree laid paper with a textured finish.

*Color* Cream

*Applications* Specially designed for prestige labels for wine, spirits and gourmet products.

*Printing techniques* Suitable for printing on conventional offset, offset UV, screen printing, hot stamping, flexo water-based, flexo solvent-base, UV flexo.

| Property               | Norm     | Units            | Value    | Tolerance |
|------------------------|----------|------------------|----------|-----------|
| Substance              | ISO 536  | g/m <sup>2</sup> | 90       | ± 4%      |
| Thickness              | ISO 534  | µm               | 123      | ± 5%      |
| Tensile strength MD/CD | ISO 1924 | kN/m             | ≥ 7/ ≥ 4 |           |

Adhesive

## A251

*Description* General use acrylic permanent adhesive including smooth and slightly rough or curved surfaces.

*Shelf life* From the date of manufacture 2 years in 20°C and RH 50%

| Property                                 | Norm  | Units  | Value | Tolerance |
|------------------------------------------|-------|--------|-------|-----------|
| Adhesion (Peel 180° 20'/stainless steel) | FTM 1 | N/25mm | 15,4  | ≥ 7,8     |
| Tack (Quick Stick stainless steel)       | FTM 9 | N      | 10,3  | ≥ 7,8     |
| Shear (1kg, in <sup>2</sup> /glass)      | FTM 8 | min    | 100   | ≥ 60      |
| Minimum labelling temperature            |       | °C     | +5    |           |
| Minimum service temperature              |       | °C     | -20   |           |
| Maximum service temperature.             |       | °C     | +80   |           |

Liner

## Glassine Ambar 62

*Description* Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

*Color* Yellow

| Property  | Norm    | Units            | Value | Tolerance |
|-----------|---------|------------------|-------|-----------|
| Substance | ISO 536 | g/m <sup>2</sup> | 56    | 55-57     |
| Thickness | ISO 534 | µ                | 48    | 46 - 49   |

• Values are subject to change without notice. Last updated 01/01/2024.

• The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards ISO 14001 and EMAS and has successfully completed audits for ISO 50001, ISO 9001 and ISO 45001 certification. Adestor paper products are available with PEFC and FSC® C011032 chain of custody certificates upon request.