

Gloss GP 80 / SP123 / GA62

Facestock

Gloss GP

Description Gloss coated woodfree paper chemically treated to protect against grease and oil.

Applications Specially indicated for food packaging and any labels requiring a barrier against grease and oil.

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), conventional offset, offset UV, screen printing, laser, thermal transfer.

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	80	± 4%
Thickness	ISO 534	µm	71	65-77
Tensile strength MD/CD	ISO 1924	kN/m	≥ 4.7 / ≥ 2.2	

Adhesive

SP123

Description Acrylic super-permanent adhesive with high tack. For difficult surfaces such as wood, some cardboards and plastics such as HDPE, PP, PET and PVC.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	17,2	≥ 13,5
Tack (Quick Stick stainless steel)	FTM 9	N	11	≥ 9,8
Shear (1kg, in ² /glass)	FTM 8	min	100	≥ 60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

Liner

Glassine Ambar 62

Description Super-calendered translucent glassine paper especially designed for automatic labelling applications and photocell dispensing systems. This liner provides good tear resistance and smooth and regular thickness.

Color Yellow

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	56	55-57
Thickness	ISO 534	µ	48	46 - 49

- Values are subject to change without notice. Last updated 01/01/2024.

- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

Our self-adhesive mill is certified to the strictest environmental standards **ISO 14001 and EMAS** and has successfully completed audits for **ISO 50001, ISO 9001 and ISO 45001** certification. Adestor paper products are available with **PEFC and FSC® C011032** chain of custody certificates upon request.