

High Gloss 180 / SP123 / WK90

Facestock

High Gloss 180

Description Cast coated woodfree paper.

Printing techniques Suitable for printing on flexo (all types), letterpress (conventional and UV), offset UV, conventional offset, screen printing, stamping (hot and cold).

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	180	± 4%
Thickness	ISO 534	µm	186	± 5%
Bekk smoothness	ISO 5627	s	1050	≥ 400
Brightness ISO	ISO 2470-2	%	88	± 2
Whiteness CIE	ISO 11475	%	108	± 5
Paper gloss	Tappi T4801 om-92	%	44	± 5
Opacity	ISO 2471	%	99	-2
Tensile strength MD/CD	ISO 1924-2	kN/m	6.5/3.6	-0.6/-0.3

Adhesive

SP123

Description Acrylic super-permanent adhesive with high tack. For difficult surfaces such as wood, some cardboards and plastics such as HDPE, PP, PET and PVC.

Shelf life From the date of manufacture 2 years in 20°C and RH 50%

Property	Norm	Units	Value	Tolerance
Adhesion (Peel 180° 20'/stainless steel)	FTM 1	N/25mm	17,2	≥ 13,5
Tack (Quick Stick stainless steel)	FTM 9	N	11	≥ 9,8
Shear (1kg, in ² /glass)	FTM 8	min	100	≥ 60
Minimum labelling temperature		°C	+5	
Minimum service temperature		°C	-20	
Maximum service temperature.		°C	+80	

Liner

Kraft White 90

Description One-side coated white liner: good stiffness and high dimensional stability for varying temperatures. Available in solid and split back.

Color White

Property	Norm	Units	Value	Tolerance
Substance	ISO 536	g/m ²	90	± 4%
Thickness	ISO 534	µm	90	± 4
Tensile strength MD/CD	ISO 1924-2	kN/m	5,2/2,6	-0,6/-0,3

- Values are subject to change without notice. Last updated 01/01/2024.

- The technical information that appears in this document reflects our knowledge and experience, but should only be considered as a general guideline.

TECHNICAL SPECIFICATIONS

*Our self-adhesive mill is certified to the strictest environmental standards **ISO 14001 and EMAS** and has successfully completed audits for **ISO 50001, ISO 9001 and ISO 45001** certification. Adestor paper products are available with **PEFC and FSC®** C011032 chain of custody certificates upon request.*